



Chemical Resistance Guide

For use with UltraTech Flourinated SpillPallets and SpillDecks

This report is offered as a guide and was developed from information which, to the best of UltraTech's knowledge, was reliable and accurate. Due to variables and conditions of application beyond UltraTech's control, none of the data shown in this guide is to be construed as a guarantee, expressed, or implied. UltraTech assumes no responsibility, obligation, or liability in conjunction with the use or misuse of information herein.

KEY

- A** = Resistant (up to 0.5% permeation)
- B** = Variable resistance (up to 2% permeation)
- C** = Not Recommended

Chemical	Test Notes	70 °F	130 ° F
Acetone		A	-
Acetic Acid	60%	A	B
Aluminum Chloride	< = 100%	A	A
Amyl Alcohol	< = 100%	B	B
Boric Acid	< = 100%	A	A
n-Butyl Alcohol	< = 100%	A	A
Calcium Chloride	Saturated solution	A	A
Carbon Disulfide		B	-
Copper Chloride	Saturated solution	A	A
Cutting Oils		A	A
Dimethylamine		A	A
Ethyl Acetate		A	A
Ethyl Ether		A	A
Gasoline		A	A
Hydrochloric Acid	< = 100%	A	A
Hydrofluoric Acid	60%	A	A
Hydrogen Peroxide	30%	A	A
Methyl Alcohol	< = 100%	A	A
Methyl Ethyl Ketone	< = 100%	A	A
Methylene Chloride	< = 100%	A	A
Mineral Oils		A	A
Naptha		A	A
Nitrobenzene	< = 100%	A	A
Perchloroethylene		A	A
Petroleum Oils		A	A
Potassium Cyanide	Saturated solution	A	A
Propylene Glycol		A	A
Sodium Hydroxide	Saturated solution	A	A
Sodium Hypochlorite		A	A
Sulfuric Acid	0 - 50%	A	A
Sulfuric Acid	70%	A	B
Sulfuric Acid	98%	B	B
Sulfuric Acid	Fuming	B	B
Tetrahydrofuran		A	A
Toluene		A	A
Trichlorethylene		A	A
Turpentine		A	A
Water		A	A